

Technical datasheet No.: 1484.10

4308 4952

marine sunprotect 390 AC

PROPERTIES		
Type of coating	ACRYLIC one side	
Finish	impregnated, containing an antimicrobial additive to protect the product long term from microbial/fungal degradation, dirt repellent	
Total weight	390 g/m ²	EN ISO 2286-2
Tensile strength warp/weft	2300 / 1400 N/50 mm	EN ISO 1421/V1
Tear strength warp/weft	400 / 300 N	DIN EN 17679
Light fastness	≥7 Note, Value	EN ISO 105 B02
Weather fastness	≥7 Note, Value	EN ISO 105 B04
Resistancy against water pressure	80-100 hPa	DIN EN ISO 811
Material	PES	DIN EN ISO 2076
Weave	RQ 2/2	
for base fabric	100 % PES endless, coloured by spin nozzle, taslanized	
Remarks	always assamble with coated side inside	



The technical data are approximate values based on average values determined. For manufacturing reasons, deviations of up to -5% are possible. These technical specifications respond to the current state of knowledge and are intended to provide information about our products without legal obligation. These data apply to new goods. Suggested applications do not release the buyer from the obligation to check whether the material is suitable for the intended use.

Version 03.2026

Bei den technischen Daten handelt es sich um ca. Werte, die auf Basis von ermittelten Durchschnittswerten erstellt wurden. Aus fertigungstechnischen Gründen sind Abweichungen bis zu -5% möglich. Diese technischen Angaben entsprechen dem heutigen Stand der Kenntnisse und sollen über unsere Produkte ohne Rechtsverbindlichkeit informieren. Diese Daten gelten für neue Ware. Einsatzvorschläge entbinden den Käufer nicht, selbst zu prüfen, ob das Material für den von ihm gewünschten Einsatz geeignet ist.

MehlerHeytex · Mehler Technologies GmbH · Rheinstraße 11 · 41836 Hückelhoven · Germany · meherheytex@freudenberg-pm.com ·

QM-071/3-08/00

EA/007-06/98

VL/LB:

Date

21.10.2026

MehlerHeytex

a brand of  FREUDENBERG