TECHNICAL DATA SHEET

Technical datasheet No.: 1238.9

7809 5340

dockshelter 3700 twin multi

PROPERTIES		
Type of coating	PVC	
Burning behaviour	ISO 3795 <100 mm/min.	
Total weight	3800 g/m²	EN ISO 2286-2
Thickness	ca. 3 mm	DIN EN ISO 2286-3
Tensile strength warp/weft	6000 / 5000 N/50 mm	EN ISO 1421/V1
Tear strength warp/weft	1000 / 900 N	DIN EN 17679
Adhesion	15 N/cm	PA 09.03 (intern)
Cold resistance	-25 °C	EN 1876-1
High Temperature	+70 °C	PA 07.04 (intern)
Light fastness	>6 Note, Value	EN ISO 105 B02
Material	PES	DIN EN ISO 2076
Yarn count	1100 dtex	DIN EN ISO 2060
Weave	P 2/2	ISO 3572
Remarks	stiffness grade 4	

The technical data are approximate values based on average values determined. For manufacturing reasons, deviations of up to -5% are possible. These technical specifications respond to the current state of knowledge and are intended to provide information about our products without legal obligation. These data apply to new goods. Suggested applications do not release the buyer from the obligation to check whether the material is suitable for the intended use.

Bei den technischen Daten handelt es sich um ca. Werte, die auf Basis von ermittelten Durchschnittswerten erstellt wurden. Aus fertigungstechnischen Gründen sind Abweichungen bis zu -5% möglich. Diese technischen Angaben entsprechen dem heutigen Stand der Kenntnisse und sollen über unsere Produkte ohne Rechtsverbindlichkeit informieren. Diese Daten gelten für neue Ware. Einsatzvorschläge entbinden den Käufer nicht, selbst zu prüfen, ob das Material für den von ihm gewünschten Einsatz geeignet ist.

MehlerHeytex · Mehler Texnologies GmbH · Rheinstraße 11 · 41836 Hückelhoven · Germany · mehlerheytex@freudenberg-pm.com ·

Version 03.2026

VL/LB:

QM-071/3-08/00 EA/007-06/98 Date 06.10.2026

MehlerHeytex

a brand of FREUDENBERG