

Technical datasheet No.: 1141.9

8250 5241

tarp 620 LQ

PROPERTIES			
Type of coating	PVC		
Finish	one side lacquered (high gloss)		
Burning behaviour	ISO 3795 <100 mm/min.		
Total weight	620 g/m ²		EN ISO 2286-2
Tensile strength	warp/weft	2500 / 2500 N/50 mm	EN ISO 1421/V1
Tear strength	warp/weft	250 / 250 N	DIN EN 17679
Adhesion		20 N/cm	PA 09.03 (intern)
Cold resistance		-40 °C	EN 1876-1
High Temperature		+70 °C	PA 07.04 (intern)
Light fastness		>6 Note, Value	EN ISO 105 B02
Crack resistance		no cracks 100000 x	DIN 53359 A
Material		PES	DIN EN ISO 2076
Yarn count		1100 dtex	DIN EN ISO 2060
Weave		L 1/1	ISO 3572



The technical data are approximate values based on average values determined. For manufacturing reasons, deviations of up to -5% are possible. These technical specifications respond to the current state of knowledge and are intended to provide information about our products without legal obligation. These data apply to new goods. Suggested applications do not release the buyer from the obligation to check whether the material is suitable for the intended use.

Version 03.2026

Bei den technischen Daten handelt es sich um ca. Werte, die auf Basis von ermittelten Durchschnittswerten erstellt wurden. Aus fertigungstechnischen Gründen sind Abweichungen bis zu -5% möglich. Diese technischen Angaben entsprechen dem heutigen Stand der Kenntnisse und sollen über unsere Produkte ohne Rechtsverbindlichkeit informieren. Diese Daten gelten für neue Ware. Einsatzvorschläge entbinden den Käufer nicht, selbst zu prüfen, ob das Material für den von ihm gewünschten Einsatz geeignet ist.

MehlerHeytex · Mehler Textologies GmbH · Rheinstraße 11 · 41836 Hückelhoven · Germany · meherheytex@freudenberg-pm.com ·

QM-071/3-08/00

EA/007-06/98

VL/LB:

Date

14.08.2026

MehlerHeytex

a brand of  **FREUDENBERG**