

8556 5240

SIDECURTAIN 900

PROPERTIES		
Coating Beschichtung	PVC	
Total weight Gesamtgewicht	900 g/m ² 27 oz/yd ²	DIN EN ISO 2286-2
Tensile strength warp/weft Zugfestigkeit Kette/Schuss	4300 / 4000N/5 cm 491/457 lbf/inch	DIN EN ISO 1421/V1
Tear resistance warp/weft Weiterreißwiderstand Kette/Schuss	600 / 550 N 135/124 lbf	DIN EN 17679
Coating adhesion (High frequency) Haftfestigkeit (Hochfrequenzverfahren)	100 N/5 cm 11 lbf/inch	PA 09.03 (internal)
Cold resistance Kältebeständigkeit	-40 °C -40 °F	DIN EN 1876-1
Heat resistance Wärmebeständigkeit	+70 °C -158 °F	PA 07.04 (internal)
Light fastness Lichtechtheit	>6 Note, Value	DIN EN ISO 105 B02
Flex resistance Knickverhalten	no cracks 100000 x keine Risse 100000 x	DIN 53359 A / DIN EN ISO 7854 B
Attributes Eigenschaft	Both sides high gloss lacquered beidseitig Hochglanz-lackiert	

The technical data are approximate values based on average values determined. For manufacturing reasons, deviations of up to -5% are possible. These technical specifications respond to the current state of knowledge and are intended to provide information about our products without legal obligation. These data apply to new goods. Suggested applications do not release the buyer from the obligation to check whether the material is suitable for the intended use.

Bei den technischen Daten handelt es sich um ca. Werte, die auf Basis von ermittelten Durchschnittswerten erstellt wurden. Aus fertigungstechnischen Gründen sind Abweichungen bis zu -5% möglich. Diese technischen Angaben entsprechen dem heutigen Stand der Kenntnisse und sollen über unsere Produkte ohne Rechtsverbindlichkeit informieren. Diese Daten gelten für neue Ware. Einsatzvorschläge entbinden den Käufer nicht, selbst zu prüfen, ob das Material für den von ihm gewünschten Einsatz geeignet ist.

MehlerHeytex · Mehler Textologies GmbH · Rheinstraße 11 · 41836 Hückelhoven · Germany · mehlerheytex@freudenberg-pm.com

Version 03/2026

MehlerHeytex

a brand of  FREUDENBERG